

Material Datasheet

Alloy 410S Stainless Steel

UNS: S41008
EN DIN: 1.4000

Description: 410S Stainless Steel is a non-hardening modification of Type 410. Small alloying additions minimize austenite formation at high temperatures, thereby restricting the alloy's ability to harden. The result is a ductile condition when the material is rapidly cooled from above the critical temperature. This non-hardening characteristic also hinders formation of cracks when the steel is welded. The alloy is completely ferritic in the annealed condition.

Applications include: Distillation trays, Heat exchangers, Annealing boxes

Industries supplied include: Oil & Gas, Chemical Processing, General Manufacturing

Nominal Composition

	C	Mn	P	S	Si	Cr	Ni	Ti	Fe
min	-	-	-	-	-	11.50	-	-	BAL
max	.080	1.0	0.040	0.030	1.00	13.50	0.60	0.20	-

Physical Properties

	At 70°F	At 20°C
Density	0.280 lb/in ³	7.73 g/cm ³
Modulus of Elasticity (E)	29.0 x 10 ³ ksi	200 GPa
Coefficient of Expansion	6.0 μin/in-°F (32-212°F)	10.8 μm/m-°C (0-100°C)
Electrical Resistivity	23.7 μohm-in	60 μohm-cm
Thermal Conductivity	187 Btu-in/ft ² -hr- °F (212°F)	26.9 W/m-K (100°C)


Applicable Specifications

Strip & Sheet | ASTM A240

Typical Mechanical Properties Typical Room Temperature Mechanical Properties

Condition	Tensile Strength (UTS)	0.2% Offset Yield	Elongation in 2" (50.8 mm)	Hardness Rockwell
Annealed	65 ksi (448 MPa)	40 ksi (276 MPa)	30%	75 HRBW

Typical mechanical properties are based on ASTM A240



WWW.ELGILOY.COM

LIMITATION OF LIABILITY AND DISCLAIMER OF WARRANTY:

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed, however, Elgiloy Specialty Metals does not recommend or endorse any material for any particular end use or application.

In no event will Elgiloy Specialty Metals be liable for any damages whatsoever arising from the use of the information included in the data sheets.

The data included in this data sheet are typical values and may vary.

Elgiloy Specialty Metals makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.